

PRODUCT DATA SHEET

Sikafloor®-01 Primer

SYNTHETIC RESIN PRIMER, APPLIED PRIOR TO FLOORING & TILING SYSTEMS



DESCRIPTION

Concentrated resin primer designed to be applied prior to cement & gypsum type products.

USES

Sikafloor®-01 Primer is suitable for pre-treating surfaces following the recommended preparation & dilution rates.

Sikafloor®-01 Primer enhances bond strength between the substrate and the subsequent Sika materials.

CHARACTERISTICS / ADVANTAGES

- EMICODE EC 1^{PLUS} certified (Very Low VOC)
- BLUE ANGLE certified (Eco friendly)
- Solvent-free
- Seals porous concrete
- Low consumption - high coverage
- Non-combustible
- Great penetration into porous concrete surfaces
- Can be applied over raw timber in neat form
- Suitable for application on subfloor heating systems
- Eliminates dust
- Versatile water dilution

SUSTAINABILITY

- EPD according to ISO 14025 and EN 15804
- Solvent-free according to TRGS 610

PRODUCT INFORMATION

Composition	Synthetic resin
Packaging	5L plastic bottle
Appearance / Colour	Blue
Shelf life	12 months from date of production (in closed packaging)
Storage conditions	Approximately twelve (12) months from date of manufacture when stored in its unopened original container. Store in a cool, dry place. Do not store below +5 °C. Material that has been mixed with water should be used within a week.
Density	1L = 1kg

SYSTEMS

System Structure	Porous Concrete	Timber/wood/CFC/scyon
	Sikafloor®-01 Primer (diluted)	Sikafloor®-01 Primer (neat)
	Sikafloor® material	Sikafloor®-4020 FiberLevel

APPLICATION INFORMATION

Substrates	<ul style="list-style-type: none"> ▪ Internal Cement Screeds ▪ Internal Calcium Sulphate based Screeds ▪ Internal/External Concrete ▪ Internal Timber & Chipboard Floors in raw form (no coatings)
------------	--

Mixing Ratio	Substrate	Dilution
	Normal steel trowel concrete finish (porous)	1L Sikafloor®-01 Primer : 3L water x 1 coat
	Mechanically prepared concrete (very porous)	1L Sikafloor®-01 Primer : 3L water x 2 coats
	Cement screeds (very porous)	1L Sikafloor®-01 Primer : 2L water x 2 coats
	Timber/wood/CFC/scyon	No dilution, apply neat x 1 coat

Consumption	1:3 ~ 7 - 8 m2 per mixed L 1:2 ~ 4 - 6 m2 per mixed L Average is depending on absorbency of the substrate, applicator device and mixing ratio.
-------------	--

Ambient Air Temperature	between +5 °C to 35 °C
-------------------------	------------------------

Substrate Temperature	between +5 °C to 35 °C
-----------------------	------------------------

Waiting Time / Overcoating	Before applying Flooring/Tiling systems wait
----------------------------	--

Substrate	Waiting Time
Normal absorbent substrates - Concrete	~10 - 20 min @ 23 °C Per coat
Calcium sulphate based substrates, if calciumsulphate based levelling compounds are used	~10 - 20 min @ 23 °C Per coat
Calcium sulphate based substrates, if cement based levelling compounds are used	~24 hrs @ 23 °C Per coat
Timber and chipboards floors	~2 hrs @ 23 °C Per coat

All values are approximate and subject to variation due to climatic conditions. Please refer also to the product datasheets of the cementitious levelling compounds and tile adhesives.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete should be fully cured, structurally sound, clean, dry, and free of surface contaminants and dust for Eg. Concrete must be porous and accept water penetration. Test by lightly sprinkling water on various areas of the substrate. If water penetrates, then a good bond with Sikafloor®-01 Primer can be achieved. If water beads and fails to be absorbed by the concrete surface contaminants are present then loss of adhesion may occur. Contaminates that are present should be mechanically removed before installation. Concrete must be free of efflorescence and not subject to hydro-static pressure. If the concrete substrate has efflorescence or high moisture (RH) a Sika Moisture Barrier System may be considered. Timber surfaces must be clean and freshly sanded to remove any previous coatings. Contact your local Sika office for current system information.

MIXING

Mix Sikafloor®-01 Primer at a ratio of 1:3 - 1:2 - 1:1 only with clean cool water.

APPLICATION

Apply diluted

Sikafloor®-01 Primer by way of a soft bristle broom, or long napped roller 10 – 15mm. Correct amount of mixed primer should always be applied to the prepared substrate, giving good penetration and film build. Thin applications may result in pinholing in finished surface or debonding levelling compound from the substrate.

On particularly porous surfaces where the initial prime coat is absorbed immediately, or mechanically prepared surfaces a second coat is recommended. Avoid foam during application by adding more liquid.

Apply neat

Sikafloor®-01 Primer over raw timber/chipboard with a long napped roller 10 – 15mm.

Note: For best practice it is recommended subsequent construction materials are applied as soon as primer is dry, but no latter than 24hrs.

- Do not allow primer to pool while drying as this will cause a soft spot under the cement compound.
- Do not allow dust to settle on the surface.
- If dust has contaminated the surface, first vacuum clean and apply another coat of primer before subsequent materials are installed.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48



Product Data Sheet

Sikafloor®-01 Primer

February 2020, Version 06.01

020815120010000042

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use.

BASIS OF PRODUCT DATA

Made in Germany. Packed in Australia.

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sikafloor-01Primer-en-AU-(02-2020)-6-1.pdf